

1576--A

2013-2014 Regular Sessions

I N   S E N A T E

(PREFILED)

January 9, 2013

---

Introduced by Sen. PARKER -- read twice and ordered printed, and when printed to be committed to the Committee on Environmental Conservation -- recommitted to the Committee on Environmental Conservation in accordance with Senate Rule 6, sec. 8 -- committee discharged, bill amended, ordered reprinted as amended and recommitted to said committee

AN ACT to amend the environmental conservation law and the general business law, in relation to jewelry containing lead

THE PEOPLE OF THE STATE OF NEW YORK, REPRESENTED IN SENATE AND ASSEMBLY, DO ENACT AS FOLLOWS:

1     Section 1. Legislative findings. The legislature hereby finds that  
2     stringent controls on the amount of lead in jewelry are necessary to  
3     protect public health, especially the health of children. Random  
4     samples of jewelry in New York state have been found to contain up to  
5     60,000 parts per million of lead. To assure consistent application of  
6     these controls to all jewelry, specific technical standards and controls  
7     must be specified.  
8     S 2. The environmental conservation law is amended by adding a new  
9     section 37-0115 to read as follows:  
10    S 37-0115. LEAD-CONTAINING JEWELRY.  
11    FOR PURPOSES OF THIS SECTION, THE FOLLOWING TERMS SHALL HAVE THE  
12    FOLLOWING DEFINITIONS:  
13    1. "BODY PIERCING JEWELRY" MEANS ANY PART OF JEWELRY THAT IS MANUFAC-  
14    TURED OR SOLD FOR PLACEMENT IN A NEW PIERCING OR A MUCOUS MEMBRANE, BUT  
15    DOES NOT INCLUDE ANY PART OF THAT JEWELRY THAT IS NOT PLACED WITHIN A  
16    NEW PIERCING OR A MUCOUS MEMBRANE.  
17    2. "CHILDREN" MEANS CHILDREN AGED SIX AND YOUNGER.  
18    3. "CHILDREN'S JEWELRY" MEANS JEWELRY THAT IS MADE FOR, MARKETING FOR  
19    USE BY, OR MARKETING TO, CHILDREN. CHILDREN'S JEWELRY INCLUDES, BUT IS  
20    NOT LIMITED TO, JEWELRY THAT MEETS ANY OF THE FOLLOWING CONDITIONS:

EXPLANATION--Matter in *ITALICS* (underscored) is new; matter in brackets [ ] is old law to be omitted.

LBD02877-02-4

1 (A) REPRESENTED IN ITS PACKAGING, DISPLAY, OR ADVERTISING, AS APPRO-  
2 PRIATE FOR USE BY CHILDREN.  
3 (B) SOLD IN CONJUNCTION WITH, ATTACHED TO, OR PACKAGED TOGETHER WITH  
4 OTHER PRODUCTS THAT ARE PACKAGED, DISPLAYED, OR ADVERTISED AS APPROPRI-  
5 ATE FOR USE BY CHILDREN.  
6 (C) SIZED FOR CHILDREN AND NOT INTENDED FOR USE BY ADULTS.  
7 (D) SOLD IN ANY OF THE FOLLOWING:  
8 (1) A VENDING MACHINE.  
9 (2) RETAIL STORE, CATALOGUE, OR ONLINE WEB SITE, IN WHICH A PERSON  
10 EXCLUSIVELY OFFERS FOR SALE PRODUCTS THAT ARE PACKAGED, DISPLAYED, OR  
11 ADVERTISED AS APPROPRIATE FOR USE BY CHILDREN.  
12 (3) A DISCRETE PORTION OF A RETAIL STORE, CATALOGUE, OR ONLINE WEB  
13 SITE, IN WHICH A PERSON OFFERS FOR SALE PRODUCTS THAT ARE PACKAGED,  
14 DISPLAYED, OR ADVERTISED AS APPROPRIATE FOR USE BY CHILDREN.  
15 4. "CLASS 1 MATERIAL" MEANS ANY OF THE FOLLOWING MATERIALS:  
16 (A) STAINLESS OR SURGICAL STEEL;  
17 (B) KARAT GOLD;  
18 (C) STERLING SILVER;  
19 (D) PLATINUM, PALLADIUM, IRIDIUM, RUTHENIUM, RHODIUM OR OSMIUM;  
20 (E) NATURAL OR CULTURED PEARLS;  
21 (F) GLASS, CERAMIC, OR CRYSTAL DECORATIVE COMPONENTS, INCLUDING CAT'S  
22 EYE, CUBIC ZIRCONIA, INCLUDING CUBIC ZIRCONIUM OR CZ, RHINESTONES, AND  
23 CLOISONNE;  
24 (G) A GEMSTONE THAT IS CUT AND POLISHED FOR ORNAMENTAL PURPOSES;  
25 (H) ELASTIC, FABRIC, RIBBON, ROPE, OR STRING, UNLESS IT CONTAINS  
26 INTENTIONALLY ADDED LEAD AND IS LISTED AS A CLASS 2 MATERIAL;  
27 (I) ALL NATURAL DECORATIVE MATERIAL, INCLUDING AMBER, BONE, CORAL,  
28 FEATHERS, FUR, HORN, LEATHER, SHELL, OR WOOD, THAT IS IN ITS NATURAL  
29 STATE AND IS NOT TREATED IN A WAY THAT ADDS LEAD; AND  
30 (J) ADHESIVE.  
31 (K) THE FOLLOWING GEMSTONES ARE NOT CLASS 1 MATERIALS: ARAGONITE,  
32 BAYLDONITE, BOLEITE, CERUSSITE, CROCOITE, EKANITE, LINARITE, MIMETITE,  
33 PHOSGENITE, SAMARSKITE, VANADINITE, AND WULFENITE.  
34 5. "CLASS 2 MATERIAL" MEANS ANY OF THE FOLLOWING MATERIALS:  
35 (A) ELECTROPLATED METAL THAT MEETS THE FOLLOWING STANDARDS:  
36 (1) ON AND BEFORE AUGUST 30, 2018, A METAL ALLOY WITH LESS THAN TEN  
37 PERCENT LEAD BY WEIGHT THAT IS ELECTROPLATED WITH SUITABLE UNDER AND  
38 FINISH COATS.  
39 (2) ON AND AFTER AUGUST 31, 2018, A METAL ALLOY WITH LESS THAN SIX  
40 PERCENT LEAD BY WEIGHT THAT IS ELECTROPLATED WITH SUITABLE UNDER AND  
41 FINISH COATS; OR  
42 (B) UNPLATED METAL WITH LESS THAN 1.5 PERCENT LEAD THAT IS NOT OTHER-  
43 WISE LISTED AS A CLASS 1 MATERIAL; OR  
44 (C) PLASTIC OR RUBBER, INCLUDING ACRYLIC, POLYSTYRENE, PLASTIC BEADS  
45 AND STONES, AND POLYVINYL CHLORIDE (PVC) THAT MEETS THE FOLLOWING STAND-  
46 ARDS:  
47 (1) ON AND BEFORE AUGUST 30, 2018, LESS THAN 0.06 PERCENT (SIX HUNDRED  
48 PARTS PER MILLION) LEAD BY WEIGHT; AND  
49 (2) ON AND AFTER AUGUST 31, 2018, LESS THAN 0.02 PERCENT (TWO HUNDRED  
50 PARTS PER MILLION) LEAD BY WEIGHT; OR  
51 (D) A DYE OR SURFACE COATING CONTAINING LESS THAN 0.06 PERCENT (SIX  
52 HUNDRED PARTS PER MILLION) LEAD BY WEIGHT.  
53 6. "CLASS 3 MATERIAL" MEANS ANY PORTION OF JEWELRY THAT MEETS BOTH OF  
54 THE FOLLOWING CRITERIA:  
55 (A) IS NOT A CLASS 1 OR CLASS 2 MATERIAL; AND

(B) CONTAINS LESS THAN 0.06 PERCENT (SIX HUNDRED PARTS PER MILLION) LEAD BY WEIGHT.

7. "COMPONENT" MEANS ANY PART OF JEWELRY.

8. "EPA REFERENCE METHODS 3050B (ACID DIGESTION OF SEDIMENTS, SLUDGES AND SOILS) OR 3051 (MICROWAVE ASSISTED DIGESTION/SLUDGE, SOILS)" MEANS THOSE TEST METHODS INCORPORATED BY REFERENCE IN PARAGRAPH ELEVEN OF SUBDIVISION (A) OF SECTION 260.11 OF TITLE 40 OF THE CODE OF FEDERAL REGULATIONS.

9. "JEWELRY" MEANS:

(A) ANY OF THE FOLLOWING ORNAMENTS WORN BY A PERSON: AN ANKLET, ARM CUFF, BRACELET, BROOCH, CHAIN, CROWN, CUFF LINK, DECORATED HAIR ACCESSORIES, EARRING, NECKLACE, PIN, RING, OR BODY PIERCING JEWELRY; OR

(B) ANY BEAD, CHAIN, LINK, PENDANT, OR OTHER COMPONENT OF SUCH AN ORNAMENT.

10. (A) "SURFACE COATING" MEANS A FLUID, SEMIFLUID, OR OTHER MATERIAL, WITH OR WITHOUT A SUSPENSION OF FINELY DIVIDED COLORING MATTER, THAT CHANGES TO A SOLID FILM WHEN A THIN LAYER IS APPLIED TO A METAL, WOOD, STONE, PAPER, LEATHER, CLOTH, PLASTIC, OR OTHER SURFACE.

(B) "SURFACE COATING" DOES NOT INCLUDE A PRINTING INK OR A MATERIAL THAT ACTUALLY BECOMES A PART OF THE SUBSTRATE, INCLUDING, BUT NOT LIMITED TO, PIGMENT IN A PLASTIC ARTICLE, OR A MATERIAL THAT IS ACTUALLY BONDED TO THE SUBSTRATE, SUCH AS BY ELECTROPLATING OR CERAMIC GLAZING.

11. ON OR AFTER MARCH 1, 2017, NO PERSON SHALL ADVERTISE, MANUFACTURE, OFFER FOR SALE, SELL, OR DISTRIBUTE FOR PROMOTIONAL PURPOSES IN THIS STATE, OR IMPORT FOR DISTRIBUTION OR SALE IN THIS STATE, ANY JEWELRY UNLESS THE JEWELRY IS MADE ENTIRELY FROM A CLASS 1, CLASS 2, OR CLASS 3 MATERIAL, OR ANY COMBINATION THEREOF.

12. NOTWITHSTANDING SUBDIVISION ELEVEN OF THIS SECTION, ON OR AFTER JANUARY 1, 2017, NO PERSON SHALL ADVERTISE, MANUFACTURE, OFFER FOR SALE, SELL, OR DISTRIBUTE FOR PROMOTIONAL PURPOSES IN THIS STATE, OR IMPORT FOR DISTRIBUTION OR SALE IN THIS STATE, ANY CHILDREN'S JEWELRY UNLESS THE CHILDREN'S JEWELRY IS MADE ENTIRELY FROM ONE OR MORE OF THE FOLLOWING MATERIALS:

(A) A NONMETALLIC MATERIAL THAT IS A CLASS 1 MATERIAL;

(B) A NONMETALLIC MATERIAL THAT IS A CLASS 2 MATERIAL;

(C) A METALLIC MATERIAL THAT IS EITHER A CLASS 1 MATERIAL OR CONTAINS LESS THAN 0.06 PERCENT (SIX HUNDRED PARTS PER MILLION) LEAD BY WEIGHT;

(D) GLASS OR CRYSTAL DECORATIVE COMPONENTS THAT WEIGH IN TOTAL NO MORE THAN ONE GRAM, EXCLUDING ANY GLASS OR CRYSTAL DECORATIVE COMPONENT THAT CONTAINS LESS THAN 0.02 PERCENT (TWO HUNDRED PARTS PER MILLION) LEAD BY WEIGHT AND HAS NO INTENTIONALLY ADDED LEAD;

(E) PRINTING INK OR CERAMIC GLAZE THAT CONTAINS LESS THAN 0.06 PERCENT (SIX HUNDRED PARTS PER MILLION) LEAD BY WEIGHT; OR

(F) CLASS 3 MATERIAL THAT CONTAINS LESS THAN 0.02 PERCENT (TWO HUNDRED PARTS PER MILLION) LEAD BY WEIGHT.

13. NOTWITHSTANDING SUBDIVISION 11 OF THIS SECTION, ON OR AFTER MARCH 1, 2017, NO PERSON SHALL ADVERTISE, MANUFACTURE, OFFER FOR SALE, SELL, OR DISTRIBUTE FOR PROMOTIONAL PURPOSES IN THIS STATE, OR IMPORT FOR DISTRIBUTION OR SALE IN THIS STATE, ANY BODY PIERCING JEWELRY UNLESS THE BODY PIERCING JEWELRY IS MADE OF ONE OR MORE OF THE FOLLOWING MATERIALS: SURGICAL IMPLANT STAINLESS STEEL, SURGICAL IMPLANT GRADE OF TITANIUM, NIOBIUM (NB), SOLID FOURTEEN KARAT OR HIGHER WHITE OR YELLOW NICKEL-FREE GOLD, SOLID PLATINUM, OR A DENSE LOW-POROSITY PLASTIC, INCLUDING, BUT NOT LIMITED TO, TYGON OR POLYTETRAFLUOROETHYLENE (PTFE), IF THE PLASTIC CONTAINS NO INTENTIONALLY ADDED LEAD.

1 S 3. The environmental conservation law is amended by adding a new  
2 section 37-0117 to read as follows:

3 S 37-0117. TESTING METHODS FOR DETERMINING COMPLIANCE WITH SECTION  
4 37-0115.

5 1. THE TESTING METHODS FOR DETERMINING COMPLIANCE WITH SECTION 37-0115  
6 OF THIS TITLE SHALL BE CONDUCTED USING THE EPA REFERENCE METHODS 3050B  
7 OR 3051 FOR THE MATERIAL BEING TESTED, EXCEPT AS OTHERWISE PROVIDED IN  
8 SUBPARAGRAPHS FIVE AND SIX OF PARAGRAPH (E) OF SUBDIVISION TWO OF THIS  
9 SECTION, AND IN ACCORDANCE WITH ALL OF THE FOLLOWING PROCEDURES:

10 (A) WHEN PREPARING A SAMPLE, THE LABORATORY SHALL MAKE EVERY EFFORT TO  
11 ASSURE THAT THE SAMPLE REMOVED FROM A JEWELRY PIECE IS REPRESENTATIVE OF  
12 THE COMPONENT TO BE TESTED, AND IS FREE OF CONTAMINATION FROM EXTRANEOUS  
13 DIRT AND MATERIAL NOT RELATED TO THE JEWELRY COMPONENT TO BE TESTED.

14 (B) ALL JEWELRY COMPONENT SAMPLES SHALL BE WASHED PRIOR TO TESTING  
15 USING STANDARD LABORATORY DETERGENT, RINSED WITH LABORATORY REAGENT  
16 GRADE DEIONIZED WATER, AND DRIED IN A CLEAN AMBIENT ENVIRONMENT.

17 (C) IF A COMPONENT IS REQUIRED TO BE CUT OR SCRAPED TO OBTAIN A  
18 SAMPLE, THE METAL SNIPS, SCISSORS, OR OTHER CUTTING TOOLS USED FOR THE  
19 CUTTING OR SCRAPING SHALL BE MADE OF STAINLESS STEEL AND WASHED AND  
20 RINSED BEFORE EACH USE AND BETWEEN SAMPLES.

21 (D) A SAMPLE SHALL BE DIGESTED IN A CONTAINER THAT IS KNOWN TO BE FREE  
22 OF LEAD AND WITH THE USE OF AN ACID THAT IS NOT CONTAMINATED BY LEAD,  
23 INCLUDING ANALYTICAL REAGENT GRADE DIGESTION ACIDS AND REAGENT GRADE  
24 DEIONIZED WATER.

25 (E) METHOD BLANKS, CONSISTING OF ALL REAGENTS USED IN SAMPLE PREPARA-  
26 TION HANDLED, DIGESTED, AND MADE TO VOLUME IN THE SAME EXACT MANNER AND  
27 IN THE SAME CONTAINER TYPE AS SAMPLES, SHALL BE TESTED WITH EACH GROUP  
28 OF TWENTY OR FEWER SAMPLES TESTED.

29 (F) THE RESULTS FOR THE METHOD BLANKS SHALL BE REPORTED WITH EACH  
30 GROUP OF SAMPLE RESULTS, AND SHALL BE BELOW THE STATED REPORTING LIMIT  
31 FOR SAMPLE RESULTS TO BE CONSIDERED VALID.

32 2. IN ADDITION TO THE REQUIREMENTS OF SUBDIVISION ONE OF THIS SECTION,  
33 THE FOLLOWING PROCEDURES SHALL BE USED FOR TESTING THE FOLLOWING MATE-  
34 RIALS:

35 (A) FOR TESTING A METAL PLATED WITH SUITABLE UNDERCOATS AND FINISH  
36 COATS, THE FOLLOWING PROTOCOLS SHALL BE OBSERVED:

37 (1) DIGESTION SHALL BE CONDUCTED USING HOT CONCENTRATED NITRIC ACID  
38 WITH THE OPTION OF USING HYDROCHLORIC ACID OR HYDROGEN PEROXIDE.

39 (2) THE SAMPLE SIZE SHALL BE 0.050 GRAM TO ONE GRAM.

40 (3) THE DIGESTED SAMPLE MAY REQUIRE DILUTION PRIOR TO ANALYSIS.

41 (4) THE DIGESTION AND ANALYSIS SHALL ACHIEVE A REPORTED DETECTION  
42 LIMIT NO GREATER THAN 0.1 PERCENT FOR SAMPLES.

43 (5) ALL NECESSARY DILUTIONS SHALL BE MADE TO ENSURE THAT MEASUREMENTS  
44 ARE MADE WITHIN THE CALIBRATED RANGE OF THE ANALYTICAL INSTRUMENT.

45 (B) FOR TESTING UNPLATED METAL AND METAL SUBSTRATES THAT ARE NOT A  
46 CLASS 1 MATERIAL THE FOLLOWING PROTOCOLS SHALL BE OBSERVED:

47 (1) DIGESTION SHALL BE CONDUCTED USING HOT CONCENTRATED NITRIC ACID  
48 WITH THE OPTION OF USING HYDROCHLORIC ACID AND HYDROGEN PEROXIDE.

49 (2) THE SAMPLE SIZE SHALL BE 0.050 GRAM TO ONE GRAM.

50 (3) THE DIGESTED SAMPLE MAY REQUIRE DILUTION PRIOR TO ANALYSIS.

51 (4) THE DIGESTION AND ANALYSIS SHALL ACHIEVE A REPORTED DETECTION  
52 LIMIT NO GREATER THAN 0.01 PERCENT FOR SAMPLES.

53 (5) ALL NECESSARY DILUTIONS SHALL BE MADE TO ENSURE THAT MEASUREMENTS  
54 ARE MADE WITHIN THE CALIBRATED RANGE OF THE ANALYTICAL INSTRUMENT.

55 (C) FOR TESTING POLYVINYL CHLORIDE (PVC), THE FOLLOWING PROTOCOLS  
56 SHALL BE OBSERVED:

(1) THE DIGESTION SHALL BE CONDUCTED USING HOT CONCENTRATED NITRIC ACID WITH THE OPTION OF USING HYDROCHLORIC ACID AND HYDROGEN PEROXIDE.

(2) THE SAMPLE SIZE SHALL BE A MINIMUM OF 0.05 GRAM IF USING MICROWAVE DIGESTION OR 0.5 GRAM IF USING HOTPLATE DIGESTION, AND SHALL BE CHOPPED OR COMMINUTED PRIOR TO DIGESTION.

(3) DIGESTED SAMPLES MAY REQUIRE DILUTION PRIOR TO ANALYSIS.

(4) DIGESTION AND ANALYSIS SHALL ACHIEVE A REPORTED DETECTION LIMIT NO GREATER THAN 0.001 PERCENT (TEN PARTS PER MILLION) FOR SAMPLES.

(5) ALL NECESSARY DILUTIONS SHALL BE MADE TO ENSURE THAT MEASUREMENTS ARE MADE WITHIN THE CALIBRATED RANGE OF THE ANALYTICAL INSTRUMENT.

(D) FOR TESTING PLASTIC OR RUBBER THAT IS NOT POLYVINYL CHLORIDE (PVC), INCLUDING ACRYLIC, POLYSTYRENE, PLASTIC BEADS, OR PLASTIC STONES, THE FOLLOWING PROTOCOLS SHALL BE OBSERVED:

(1) THE DIGESTION SHALL BE CONDUCTED USING HOT CONCENTRATED NITRIC ACID WITH THE OPTION OF USING HYDROCHLORIC ACID OR HYDROGEN PEROXIDE.

(2) THE SAMPLE SIZE SHALL BE A MINIMUM OF 0.05 GRAM IF USING MICROWAVE DIGESTION OR 0.5 GRAM IF USING HOTPLATE DIGESTION, AND SHALL BE CHOPPED OR COMMINUTED PRIOR TO DIGESTION.

(3) PLASTIC BEADS OR STONES SHALL BE CRUSHED PRIOR TO DIGESTION.

(4) DIGESTED SAMPLES MAY REQUIRE DILUTION PRIOR TO ANALYSIS.

(5) DIGESTION AND ANALYSIS SHALL ACHIEVE A REPORTED DETECTION LIMIT NO GREATER THAN 0.001 PERCENT (TEN PARTS PER MILLION) FOR SAMPLES.

(6) ALL NECESSARY DILUTIONS SHALL BE MADE TO ENSURE THAT MEASUREMENTS ARE MADE WITHIN THE CALIBRATED RANGE OF THE ANALYTICAL INSTRUMENT.

(E) FOR TESTING COATINGS ON GLASS AND PLASTIC PEARLS, THE FOLLOWING PROTOCOLS SHALL BE OBSERVED:

(1) THE COATING OF GLASS OR PLASTIC BEADS SHALL BE SCRAPED ONTO A SURFACE FREE OF DUST, INCLUDING A CLEAN WEIGHING PAPER OR PAN, USING A CLEAN STAINLESS STEEL RAZOR BLADE OR OTHER CLEAN SHARP INSTRUMENT THAT WILL NOT CONTAMINATE THE SAMPLE WITH LEAD. THE SUBSTRATE PEARL MATERIAL SHALL NOT BE INCLUDED IN THE SCRAPINGS.

(2) THE RAZOR BLADE OR SHARP INSTRUMENT SHALL BE RINSED WITH DEIONIZED WATER, WIPED TO REMOVE PARTICULATE MATTER, RINSED AGAIN, AND DRIED BETWEEN SAMPLES.

(3) THE SCRAPINGS SHALL BE WEIGHED AND NOT LESS THAN FIFTY MICROGRAMS OF SCRAPED COATING SHALL BE USED FOR ANALYSIS. IF LESS THAN FIFTY MICROGRAMS OF SCRAPED COATING IS OBTAINED FROM AN INDIVIDUAL PEARL, MULTIPLE PEARLS FROM THAT SAMPLE SHALL BE SCRAPED AND COMPOSITED TO OBTAIN A SUFFICIENT SAMPLE AMOUNT.

(4) THE NUMBER OF PEARLS USED TO MAKE THE COMPOSITE SHALL BE NOTED.

(5) THE SCRAPINGS SHALL BE DIGESTED ACCORDING TO EPA REFERENCE METHOD 3050B OR 3051 OR AN EQUIVALENT PROCEDURE FOR HOT ACID DIGESTION IN PREPARATION FOR TRACE LEAD ANALYSIS.

(6) THE DIGESTATE SHALL BE DILUTED IN THE MINIMUM VOLUME PRACTICAL FOR ANALYSIS.

(7) THE DIGESTED SAMPLE SHALL BE ANALYZED ACCORDING TO SPECIFICATION OF AN APPROVED AND VALIDATED METHODOLOGY FOR INDUCTIVELY COUPLED PLASMA MASS SPECTROMETRY.

(8) A REPORTING LIMIT OF 0.001 PERCENT (TEN PARTS PER MILLION) IN THE COATING SHALL BE OBTAINED FOR THE ANALYSIS.

(9) THE SAMPLE RESULT SHALL BE REPORTED WITHIN THE CALIBRATED RANGE OF THE INSTRUMENT. IF THE INITIAL TEST OF THE SAMPLE IS ABOVE THE HIGHEST CALIBRATION STANDARD, THE SAMPLE SHALL BE DILUTED AND REANALYZED WITHIN THE CALIBRATED RANGE OF THE INSTRUMENT.

(F) FOR TESTING DYES, PAINTS, COATINGS, VARNISH, PRINTING INKS, CERAMIC GLAZES, GLASS, OR CRYSTAL, THE FOLLOWING TESTING PROTOCOLS SHALL BE OBSERVED:

(1) THE DIGESTION SHALL USE HOT CONCENTRATED NITRIC ACID WITH THE OPTION OF USING HYDROCHLORIC ACID OR HYDROGEN PEROXIDE.

(2) THE SAMPLE SIZE SHALL BE NOT LESS THAN 0.050 GRAM, AND SHALL BE CHOPPED OR COMMINUTED PRIOR TO DIGESTION.

(3) THE DIGESTED SAMPLE MAY REQUIRE DILUTION PRIOR TO ANALYSIS.

(4) THE DIGESTION AND ANALYSIS SHALL ACHIEVE A REPORTED DETECTION LIMIT NO GREATER THAN 0.001 PERCENT (TEN PARTS PER MILLION) FOR SAMPLES.

(5) ALL NECESSARY DILUTIONS SHALL BE MADE TO ENSURE THAT MEASUREMENTS ARE MADE WITHIN THE CALIBRATED RANGE OF THE ANALYTICAL INSTRUMENT.

(G) FOR TESTING GLASS AND CRYSTAL USED IN CHILDREN'S JEWELRY, THE FOLLOWING TESTING PROTOCOLS FOR DETERMINING WEIGHT SHALL BE USED:

(1) A COMPONENT SHALL BE FREE OF ANY EXTRANEOUS MATERIAL, INCLUDING ADHESIVE, BEFORE IT IS WEIGHED.

(2) THE SCALE USED TO WEIGH A COMPONENT SHALL BE CALIBRATED IMMEDIATELY BEFORE THE COMPONENTS ARE WEIGHED USING S-CLASS WEIGHTS OF ONE AND TWO GRAMS, AS CERTIFIED BY THE NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY (NIST) OF THE DEPARTMENT OF COMMERCE.

(3) THE CALIBRATION OF THE SCALE SHALL BE ACCURATE TO WITHIN 0.01 GRAM.

3. THE COMMISSIONER MAY PROMULGATE RULES AND/OR REGULATIONS MODIFYING THE TESTING PROTOCOLS SPECIFIED IN SUBDIVISIONS ONE AND TWO OF THIS SECTION, AS SUCH COMMISSIONER DEEMS NECESSARY TO FURTHER THE PURPOSES OF THIS SECTION.

S 4. The environmental conservation law is amended by adding a new section 71-3711 to read as follows:

S 71-3711. ENFORCEMENT OF SECTION 37-0115.

1. ANY PERSON WHO VIOLATES ANY PROVISION OF OR FAILS TO PERFORM ANY DUTY IMPOSED BY SECTION 37-0115 OF THIS CHAPTER SHALL UPON THE FIRST FINDING OF SUCH A VIOLATION BE LIABLE FOR A CIVIL PENALTY NOT TO EXCEED FIVE HUNDRED DOLLARS FOR EACH VIOLATION. ANY PERSON CONVICTED OF A SECOND OR SUBSEQUENT VIOLATION SHALL BE LIABLE FOR A CIVIL PENALTY NOT TO EXCEED TWENTY-FIVE HUNDRED DOLLARS FOR EACH VIOLATION.

2. PENALTIES UNDER THIS SECTION SHALL BE ASSESSED BY THE COMMISSIONER AFTER A HEARING PURSUANT TO THE PROVISIONS OF SECTION 71-1709 OF THIS ARTICLE. IN ASSESSING THE PENALTY UNDER THIS SECTION, THE COMMISSIONER SHALL CONSIDER: THE NATURE AND EXTENT OF THE VIOLATION; THE NUMBER AND SEVERITY OF THE VIOLATIONS; THE ECONOMIC EFFECT OF THE PENALTY ON THE VIOLATOR; WHETHER THE VIOLATOR TOOK GOOD FAITH MEASURES TO COMPLY WITH THIS CHAPTER; THE WILLFULNESS OF THE VIOLATOR'S MISCONDUCT; THE DETERRENT EFFECT THAT THE IMPOSITION OF THE PENALTY WOULD HAVE ON BOTH THE VIOLATOR AND THE REGULATED COMMUNITY AS A WHOLE; AND OTHER FACTORS THAT THE COMMISSIONER DEEMS APPROPRIATE AND RELEVANT. ANY PERSON FOUND TO HAVE VIOLATED SECTION 37-0115 OF THIS CHAPTER MAY BE ENJOINED FROM CONTINUING SUCH VIOLATION.

3. ALL CIVIL PENALTIES AND FINES COLLECTED FOR ANY VIOLATION OF SECTION 37-0115 OF THIS CHAPTER SHALL BE PAID OVER TO THE COMMISSIONER FOR DEPOSIT IN THE ENVIRONMENTAL PROTECTION FUND ESTABLISHED BY SECTION NINETY-TWO-S OF THE STATE FINANCE LAW.

4. (A) NO CHARGE OF A VIOLATION OF THE PROVISIONS OF, OR FAILURE TO PERFORM A DUTY IMPOSED BY SECTION 37-0115 OF THIS CHAPTER SHALL BE BASED UPON EXCESSIVE LEAD CONTENT EXCEPT UPON A SHOWING THAT THE LABORATORY TESTS ESTABLISHING SUCH EXCESSIVE LEAD CONTENT WERE PERFORMED BY A LABO-

1 RATORY THAT COMPLIES WITH THE TESTING REQUIREMENTS ESTABLISHED BY  
2 SECTION 37-0117 OF THIS CHAPTER.

3 (B) A PERSON CHARGED WITH A VIOLATION OF THE PROVISIONS OF, OR FAILURE  
4 TO PERFORM A DUTY IMPOSED BY SECTION 37-0115 OF THIS CHAPTER SHALL BE  
5 PROVIDED WITH ALL SUPPORTING DOCUMENTATION RELATED TO THE TESTING OF THE  
6 JEWELRY, INCLUDING, BUT NOT LIMITED TO, DOCUMENTATION OF THE PROCEDURES  
7 UTILIZED BY THE LABORATORY, COPIES OF ALL TEST RESULTS, EXEMPLARS OF THE  
8 PRODUCTS TESTED TO THE EXTENT PRACTICABLE, AND SUCH OTHER DOCUMENTATION  
9 AND EVIDENCE WHICH SHALL REASONABLY BE REQUIRED TO VERIFY THE ACCURACY  
10 OF THE TEST RESULTS.

11 S 5. The general business law is amended by adding a new section 399-  
12 gg to read as follows:

13 S 399-GG. LABELING OF JEWELRY. 1. NO PERSON, FIRM OR CORPORATION SHALL  
14 SELL OR OFFER FOR SALE ANY JEWELRY, AS DEFINED BY SECTION 37-0115 OF THE  
15 ENVIRONMENTAL CONSERVATION LAW, UNLESS THERE IS PRINTED ON THE PACKAGE  
16 IN WHICH SUCH JEWELRY IS SOLD OR OFFERED FOR SALE A CONSPICUOUS NOTICE  
17 STATING THE PERCENTAGE OF LEAD CONTAINED IN SUCH JEWELRY. ANY JEWELRY  
18 CONTAINING MORE THAN 0.02 PERCENT (TWO HUNDRED PARTS PER MILLION) LEAD  
19 BY WEIGHT SHALL CONTAIN A WARNING LABEL, PROMINENTLY DISPLAYED, WHICH  
20 STATES, "CONTAINS LEAD WHICH MAY BE HARMFUL TO YOUR HEALTH. NOT TO BE  
21 USED BY CHILDREN UNDER THE AGE OF SIX."

22 2. ANY VIOLATION OF THIS SECTION SHALL BE PUNISHABLE BY A CIVIL PENAL-  
23 TY NOT TO EXCEED FIVE HUNDRED DOLLARS.

24 S 6. This act shall take effect immediately; provided, however that  
25 section five of this act shall take effect March 1, 2017.